



What is claimed is:

1. Curatives for epoxy resins characterized by being a clathrate comprising a tetrakisphenol compound represented by a general formula [I];



wherein X represents  $(CH_2)_n$ , wherein n is 0, 1, 2 or 3, and  $R^1$  to  $R^8$  each represents hydrogen, a lower alkyl, optionally-substituted phenyl, halogeno or a lower alkoxy, and a compound which reacts with the epoxy group of an epoxy resin to cure the resin.


2. Curing accelerators for epoxy resins characterized by being a clathrate comprising a tetrakisphenol compound represented by a general formula [I];



wherein X represents  $(CH_2)_n$ , wherein n is 0, 1, 2 or 3, and  $R^1$  to  $R^8$  each represents hydrogen, a lower alkyl, optionally-substituted phenyl, halogeno or a lower alkoxy, and a compound accelerating the curing of a compound which reacts with the epoxy group of an epoxy resin to cure the resin.

3. Epoxy resin compositions characterized by containing the clathrate comprising a tetrakisphenol compound represented by a general formula [I] and a compound which reacts with the epoxy group of an epoxy resin to cure the resin according to claim 1 and/or the clathrate comprising a tetrakisphenol compound represented by a general formula [I] and a compound accelerating the curing of a compound which reacts with the epoxy group of an epoxy resin to cure the resin according to claim 2.

4. Epoxy resin compositions characterized by containing a curative which reacts with the epoxy group of an epoxy resin to cure the resin and a tetrakisphenol compound represented by a general formula [I];



wherein X represents  $(CH_2)_n$ , wherein n is 0, 1, 2 or 3, and  $R^1$  to  $R^8$  each represents hydrogen, a lower alkyl, optionally-substituted phenyl, halogeno or a lower alkoxy, in an amount of from 0.001 to 0.1 mole based on 1 mole of the epoxy groups.

5. Epoxy resin compositions characterized by containing the clathrate according to claim 1 which comprises a tetrakisphenol compound represented by a general formula [I] and a compound which reacts with the epoxy group of an epoxy resin to cure the resin and the

clathrate according to claim 2 which comprises a tetrakisphenol compound represented by a general formula [I] and a compound accelerating the curing of a compound which reacts with the epoxy group of an epoxy resin to cure the resin, wherein the content of the clathrate in the resin composition is in a range of from 0.001 to 0.1 mole based on 1 mole of the epoxy groups, respectively.